


Lita

Specification according to EN 1307



Type of manufacture	ISO 2424	Needed						
Aspect	ISO 2424	Pile needle felt						
Dye method		Fibre dyed						
Dimension	EN ISO 24342	cm x cm	50 x 50 / 19,68" x 19,68" (20 tiles per box)					
Primary backing	ISO 2424	Polyester fleece						
Secondary backing	ISO 2424	DESSO ProBase Polyver®						
Pile fibre composition	ISO 2424	BCF Polyamide 6						
Total thickness	ISO 1765	mm	9.0	inch	0.4			
Effective pile thickness	ISO 1766	mm	5.0	inch	0.20			
Total mass	ISO 8543	g/m ²	4950	oz/yd ²	146.1			
Total pile mass	ISO 2424	g/m ²	1340	oz/yd ²	39.6			
Effective pile mass	ISO 8543	g/m ²	500	oz/yd ²	14.8			
Pile density	ISO 8543	g/cm ³	0.100	lb/in ³	0.0036			
Number of tufts	ISO 1763	/dm ²	-	/yd ²	-			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307	33 Commercial - heavy use						
Luxury rating	EN 1307	LC 2						
Dimensional stability	EN 986	%	≤ 0,2					
Impact sound reduction ΔL _w	ISO 10140	dB	25					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.02	0.08	0.12	0.25	0.42	0.50
Noise reduction	ISO 354	α _w	0.25					
Thermal resistance	ISO 8302	m ² .K/W	0.106					
Flammability	EN 13501-1	Bfl - s1 (loose laid tested)						
Prodis - GUT	www.pro-dis.info	AF2AF244						





EN 14041
0493-CPR-0002

Manufactured by:


Tarkett BV
Taxandriaweg 15
NL - 5142 PA Waalwijk







23





33


















Quality- and Environmental
Management System Certification
ISO 9001 & ISO 14001

Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20200113